


THERMATEX® Alpha ONE

THERMATEX® Alpha ONE is a new wet-felt mineral tile which provides highest sound absorption values. With a strong white acoustic fleece THERMATEX® Alpha ONE offers a smooth, elegant surface finish. The combination of bio-soluble mineral wool with clay and starch provides excellent physical characteristics.


SYSTEM	C Exposed Grid System, demountable ceiling
Dimensions	600 x 600 mm 1200 x 1200 mm
Please note	Additional sizes available on request
Thickness / Weight	24 mm (approx. 4.0 kg/m ²)
Colour	White similar to RAL 9010
Edge details	SK, VT24



Additional edge details available on request

TECHNICAL PERFORMANCE

Building material class	A2-s1, d0 as per EN 13501-1
Fire resistance	F30 - F90 as per DIN 4102 part 2 (as per test certificate) REI30 - REI90 per EN 13501 part 2 (as per test certificate)
Sound absorption	EN ISO 354 $\alpha_w = 1.00$ as per EN ISO 11654 NRC = 1.00 as per ASTM C 423
Sound attenuation	$D_{n,f,w} = 29$ dB as per EN ISO 10848 (24 mm thickness, according to test report)
Light reflectance	for white similar to RAL 9010 glare-free approx. 88%
Thermal conductivity	$\lambda = 0.040$ W/mK as per EN 12667
Air permeability	PM1 (≤ 30 m ³ /hm ²) as per DIN 18177
Humidity	up to 95% RH
Clean room classification	class 4 as per ISO 14644-1
Interior air	Indoor air comfort GOLD status



Knauf AMF GmbH & Co. KG
Eisenthal 15
D-94481 Grafenau Germany
Telefon 08552 / 422-0 - Fax 08552 / 422-32
info@knaufamf.de - www.knaufamf.com

Due to reproduction processes colours shown in this catalogue may differ from the actual product colour. Product selection should always be made from AMF samples. All details and technical information stated in this brochure or other publicity material referring to AMF ceiling systems are based on test reports obtained under laboratory conditions. It is the responsibility of the customer to ensure that this data is suitable for the proposed application. All information provided is based on current technical data. Further relevant test reports, assessments and installation guidelines are available. All system details conform with current standards and are based on the use of AMF products and system components. AMF accepts no liability or responsibility for use of third party components, or for any variations to conditions stipulated in test data. Mixing of production batches is not recommended. All technical data is subject to change without prior notice and is governed by AMF Terms and Conditions of Sales. This catalogue supersedes all previous editions. Errors and omissions excepted. Printing errors excepted.